

# LATEX EXAMINATION GLOVES POWDER FREE PALM TEXTURED

## Glove Specification

### Product Number

Item #	Size	Length	Inches	Palm Width
	XXS	240 ± 2 mm	9.44	65 ± 5 mm
	XS	240 ± 2 mm	9.44	75 ± 5 mm
	S	240 ± 2 mm	9.44	85 ± 5 mm
	M	240 ± 2 mm	9.44	95 ± 5 mm
	L	240 ± 2 mm	9.44	105 ± 5 mm
	XL	240 ± 2 mm	9.44	115 ± 5 mm

### Mill Thickness

All Size	Finger	Palm	Cuff
	4.4 mill	4.0 mill	3.2 mill

### Tensile Properties

	Before Aging	After Aging
Tensile Strength MPa (Minimum)	14	14
Ultimate Elongation % (Minimum)	650	500

### Performance Requirements – AQL

Item	Related Defects	Inspection	
		Level	Inspection
Water Tightness Test	Holes, Pinholes and Lumps	FDA As per 21 CFR Vol. 8 / S-4 Single Normal	1.5
Physical Dimension	Length, Width, Thickness	S - 2	4.0
Physical Properties	Before and After accelerated aging	S - 2	4.0
Visual Defect	Stains, etc.	S - 4	2.5

### Specification

Intended Use	: Medical Activities
Basic Material	: Natural Rubber Latex
FDA Status	: Class I, Medical Device with 510K
Colour	: Natural

## Material Safety Data Sheet

### Identification

- Product : Latex Examination Gloves Powder Free Palm Textured - Non Sterile
- Case # : Not Established
- IATO / IACO : Not Established
- Hazard Rating : Not Established
- D.O.T Rating : Not Established

### Physical Data

- Natural Solid Rubber : 98.05 %
- Sulfur : 0.7 %
- Zinc Oxide : 0.5 %
- Titanium Dioxide : 0.25 %
- ZDEC : 0.30 %
- ZDBC : 0.20 %
- Donning : N/A

### Fire and Explosion

- Stability : Stable
- Flash Point : N / A
- Extinguishing Media : Foam, Carbon Dioxide, Water

### Normal Precautions

- Ventilation : Not Necessary Under Normal Condition
- Equipment : Not Necessary
- Spill / Clean Up : N / A
- Eyes : N / A
- Storage :
  - No Special Precautions Necessary
  - Store at room Temperature